

Technical data sheet



JX-GTWEB-9 (Corrugated)

SPECIFICATIONS

FILTER MATERIAL		100% SYNTHETIC
PERMEABILITY	M3/M2/H AT 200 PA	650
WEIGHT	G/M2	130
ELONGATION MD	%	40
ELONGATION CD	%	45
THICKNESS IN MM	MM	0,42
PORE SIZE	MICRON	
TENSTILE STRENGTH MD	N/5CM	480
TENSTILE STRENGTH CD	N/5CM	300
TEAR STRENGTH MD	N	35
TEAR STRENGTH CD	N	30
THERMAL SHRINKAGE MD	%	3,5
THERMAL SHRIANKAGE CD	%	0,7
MULLEN BURST	KG/CM2	
TEMPERATURE RESISTANCE	C	140
HYDROPHOBIC RESISTANCE		GOOD
ACID RESISTANCE		GOOD
ALKALINE RESISTANCE		GOOD
DUST RELEASE		EXCELLENT
FILTER TEST	IFA / EN779:2012	M / F9
EFFICIENCY 0,4 MICRON – UNTREATED EFF.	%	99,7
EFFICIENCY 0,4 MICRON – DISCHARGED EFF.	%	98,8
DUST HOLDING CAPACITY	G AT 450 PA	2262,2