

# Technical data sheet



## JX130-B-C-PTFE MEMBRANE (Corrugated)

### SPECIFICATIONS

FILTERMATERIAL		100% POLYESTER
CONSTRUCTION		BICO SPUN BOND +THERMAL BONDED PTFE MEMBRANE
TREATMENT		
PERMEABILITY	M3/M2/H AT 200 PA	430
WEIGHT	G/M2	130
ELONGATION MD	%	40
ELONGATION CD	%	45
THICKNESS IN MM	MM	0,42
PORE SIZE	MICRON	
TENSTILE STRENGTH MD	N	480
TENSTILE STRENGTH CD	N	300
TEAR STRENGTH MD	N	35
TEAR STRENGTH CD	N	30
THERMAL SHRINKAGE MD	%	3,5
THERMAL SHRIANKAGE CD	%	0,7
MULLEN BURST	KG/CM2	
TEMPERATURE RESISTANCE	C	140
HYDROPHOBIC RESISTANCE		GOOD
ACID RESISTANCE		GOOD
ALKALINE RESISTANCE		GOOD
DUST RELEASE		EXCELLENT
FILTER TEST	BIA / EN779-2002	M / E 11
EFFICIENCY OF 0,4 MICRON	%	98,3