

Technical data sheet



JX130PET

SPECIFICATIONS

FILTERMATERIAL		100% POLYESTER
CONSTRUCTION		
TREATMENT		
PERMEABILITY	M3/M2/H AT 200 PA	1800-1900
WEIGHT	G/M2	130-135
ELONGATION MD	%	42,1
ELONGATION CD	%	49,7
THICKNESS IN MM	MM	0,42
PORE SIZE	MICRON	
TENSTILE STRENGTH MD	N	541,7
TENSTILE STRENGTH CD	N	350,4
TEAR STRENGTH MD	N	41,5
TEAR STRENGTH CD	N	37
THERMAL SHRINKAGE MD	%	3,2
THERMAL SHRIANKAGE CD	%	0,61
MULLEN BURST	KG/CM2	
TEMPERATURE RESISTANCE	C	120
HYDROPHOBIC RESISTANCE		FAIR
ACID RESISTANCE		GOOD
ALKALINE RESISTANCE		POOR
DUST RELEASE		FAIR
FILTER TEST	BIA / EN779-2002	
EFFICIENCY OF 0,4 MICRON	%	