

# Technical data sheet



## JX130-B

### SPECIFICATIONS

|                          |                   |                |
|--------------------------|-------------------|----------------|
| FILTERMATERIAL           |                   | 100% POLYESTER |
| CONSTRUCTION             |                   | BICO POLYESTER |
| TREATMENT                |                   |                |
| PERMEABILITY             | M3/M2/H AT 200 PA | 1000-1100      |
| WEIGHT                   | G/M2              | 130            |
| ELONGATION MD            | %                 | 30             |
| ELONGATION CD            | %                 | 35             |
| THICKNESS IN MM          | MM                | 0,45           |
| TENSTILE STRENGTH MD     | N/5CM             | 450            |
| TENSTILE STRENGTH CD     | N/5CM             | 350            |
| TEAR STRENGTH MD         | N                 | 40             |
| TEAR STRENGTH CD         | N                 | 35             |
| THERMAL SHRINKAGE MD     | %                 | 1,88           |
| THERMAL SHRIANKAGE CD    | %                 | 0,5            |
| MULLEN BURST             | KG/CM2            |                |
| TEMPERATURE RESISTANCE   | C                 | 120            |
| HYDROPHOBIC RESISTANCE   |                   | FAIR           |
| ACID RESISTANCE          |                   | GOOD           |
| ALKALINE RESISTANCE      |                   | FAIR           |
| DUST RELEASE             |                   | FAIR           |
| FILTRATION CLASS         | IFA/EN779-2009    |                |
| EFFICIENCY OF 0,4 MICRON | %                 |                |