

Technical data sheet



JX140-FR

SPECIFICATIONS

FILTERMATERIAL		20% POLYESTER + 80% CELLULOSE
CONSTRUCTION		FLAME RETARDANT
PERMEABILITY	M3/M2/H AT 200 PA	600
WEIGHT	G/M2	135
ELONGATION MD	%	22
ELONGATION CD	%	20
THICKNESS IN MM	MM	0,45
PORE SIZE	MICRON	42
TENSTILE STRENGTH MD	N	490
TENSTILE STRENGTH CD	N	375
TEAR STRENGTH MD	N	175
TEAR STRENGTH CD	N	169
THERMAL SHRINKAGE MD	%	
THERMAL SHRIANKAGE CD	%	
MULLEN BURST	KG/CM2	4,28
TEMPERATURE RESISTANCE	C	80
OLEO/HYDROPHOBIC RES.		FAIR
ACID RESISTANCE		FAIR
ALKALINE RESISTANCE		FAIR
DUST RELEASE		GOOD
FILTER TEST	BIA	M
EFFICIENCY OF 0,4 MICRON	%	39%