

Technical data sheet



JX240-B

SPECIFICATIONS

FILTERMATERIAL		100% POLYESTER
CONSTRUCTION		BICO SPUN BOND
TREATMENT		
PERMEABILITY	M3/M2/H AT 200 PA	699
WEIGHT	G/M2	240
ELONGATION MD	%	35
ELONGATION CD	%	35
THICKNESS IN MM	MM	0,60
PORE SIZE	MICRON	1,2
TENSTILE STRENGTH MD	N	1000
TENSTILE STRENGTH CD	N	850
TEAR STRENGTH MD	N	70
TEAR STRENGTH CD	N	60
THERMAL SHRINKAGE MD	%	2,0
THERMAL SHRIANKAGE CD	%	0,9
MULLEN BURST	KG/CM2	35
TEMPERATURE RESISTANCE	C	120
HYDROPHOBIC RESISTANCE		GOOD
ACID RESISTANCE		GOOD
ALKALINE RESISTANCE		FAIR
DUST RELEASE		GOOD
FILTER TEST	DIN EN 60335-2-69-2010	M
EFFICIENCY OF 0,3 MICRON	%	