

# Technical data sheet



## JX255-B-HO (Both sides) + PTFE MEMBRANE

### SPECIFICATIONS

FILTERMATERIAL		100% POLYESTER
CONSTRUCTION		BICO SPUN BOND + THERMAL BONDED PTFE MEMBRANE
TREATMENT (BOTH SIDES)	OLEO/HYDROPHOBIC	
PERMEABILITY	M3/M2/H AT 200 PA	250
WEIGHT	G/M2	270
ELONGATION MD	%	17,6
ELONGATION CD	%	16,8
THICKNESS IN MM	MM	0,56
PORE SIZE	MICRON	1,2
TENSTILE STRENGTH MD	N/5CM	900
TENSTILE STRENGTH CD	N/5CM	700
TEAR STRENGTH MD	N	300
TEAR STRENGTH CD	N	280
THERMAL SHRINKAGE MD	%	0,8
THERMAL SHRIANKAGE CD	%	0,5
MULLEN BURST	KG/CM2	35
TEMPERATURE RESISTANCE	C	120
HYDROPHOBIC RESISTANCE		EXCELLENT
ACID RESISTANCE		GOOD
ALKALINE RESISTANCE		GOOD
DUST RELEASE		EXCELLENT
FILTER TEST	BIA / EN779-2002	M / E11*
EFFICIENCY OF 0,4 MICRON	%	99,2*

\*BIA AND EN779-2002 DATA TAKEN FROM JX255-B-PTFE MEMBRANE.

JP Air Tech · Narvikvej 7, DK-4900 Nakskov · Denmark  
Phone +45 5495 0025 · VAT No. DK 25054342 · Mail: sales@jpairtech.com

[www.jpairtech.com](http://www.jpairtech.com)