

Technical data sheet



JX260-B

SPECIFICATIONS

| | | |
|--------------------------|-------------------|----------------|
| FILTERMATERIAL | | 100% POLYESTER |
| CONSTRUCTION | | BICO SPUN BOND |
| TREATMENT | | |
| PERMEABILITY | M3/M2/H AT 200 PA | 500-600 |
| WEIGHT | G/M2 | 260 |
| ELONGATION MD | % | 17,6 |
| ELONGATION CD | % | 16,8 |
| THICKNESS IN MM | MM | 0,56 |
| PORE SIZE | MICRON | 1,2 |
| TENSTILE STRENGTH MD | N | 900 |
| TENSTILE STRENGTH CD | N | 700 |
| TEAR STRENGTH MD | N | 300 |
| TEAR STRENGTH CD | N | 280 |
| THERMAL SHRINKAGE MD | % | 0,8 |
| THERMAL SHRIANKAGE CD | % | 0,5 |
| MULLEN BURST | KG/CM2 | 35 |
| TEMPERATURE RESISTANCE | C | 120 |
| HYDROPHOBIC RESISTANCE | | GOOD |
| ACID RESISTANCE | | GOOD |
| ALKALINE RESISTANCE | | FAIR |
| DUST RELEASE | | GOOD |
| FILTER TEST | BIA | |
| EFFICIENCY OF 0,3 MICRON | % | |