

# Technical data sheet



## JX260PET-HO

### SPECIFICATIONS

FILTERMATERIAL		100% POLYESTER
CONSTRUCTION		SPUNDBOND
TREATMENT		OLEO/HYDROPHOBIC
PERMEABILITY	M3/M2/H AT 200 PA	408
WEIGHT	G/M2	260
ELONGATION MD	%	18,6
ELONGATION CD	%	24,8
THICKNESS IN MM	MM	0,54
FIBER SIZE	DENIER	1,2-2,7
TENSTILE STRENGTH MD	N	512,4
TENSTILE STRENGTH CD	N	518,3
TEAR STRENGTH MD	N	386,7
TEAR STRENGTH CD	N	358,2
THERMAL SHRINKAGE MD	%	0,67
THERMAL SHRIANKAGE CD	%	0,32
MULLEN BURST	KG/CM2	25
TEMPERATURE RESISTANCE	C	120
OLEO/HYDROPHOBIC RESIST.		EXCELLENT
ACID RESISTANCE		GOOD
ALKALINE RESISTANCE		GOOD
DUST RELEASE		EXCELLENT
FILTER TEST	BIA	M
EFFICIENCY OF 0,3 MICRON	%	48