



2820 S. English Station Road - Louisville, KY 40299

TEST NO. 15-0828


EN 779-2002 Initial Efficiency

Flat Sheet Initial Efficiency Test

page 1 of 2

Filter Description	Manufacturer	JP Ait Tech
	Filter Model	JX135 Nano-10
	Nominal Face Dimensions	24" X 24"
	Media Type	Flat Sheet
Test Conditions	Test Air Flow Rate (FPM)	10.5
	Challenge Aerosol	DEHS
	Test Air Temp (degrees F.)	75.3
	Relative Humidity (%)	45.3
	Barometric Pressure (In. Hg.)	29.21
Test Results	Initial Resistance (Inches Water Gage)	0.29
	0.35 Micron Range Efficiency	76.13%
	0.45 Micron Range Efficiency	83.64%
	0.55 Micron Range Efficiency	87.86%
	0.69 Micron Range Efficiency	90.73%
	0.89 Micron Range Efficiency	92.28%
	1.22 Micron Range Efficiency	93.38%
	1.73 Micron Range Efficiency	95.37%
	2.45 Micron Range Efficiency	99.00%
	3.46 Micron Range Efficiency	99.93%
Average Efficiency at 0.4 micrometers 79.89%		

Efficiency vs. particle size




Requestor Information	Test Requestor	Joergen Poulsen	Phone Number	45-5495-25
	Company Name	JP Air Tech	Email	jp@jpairtech.com
	Company Address	Narvikvej 7 DK-4900; Denmark	Date Requested	6/5/2015
Test Operator Information	Test Performed by:	Glen Toloczko CAFS	Completion Date	6/12/2015


EN 779-2002 Initial Resistance

Flat Sheet Initial Resistance Test

Filter Description	Manufacturer	<u>JP Ait Tech</u>				
	Filter Model	<u>JX135 Nano-10</u>				
	Nominal Face Dimensions	<u>24" X 24"</u>				
	Media Type	<u>Flat Sheet</u>				
Test Conditions	Test Air Flow Rate (FPM)	<u>10.5</u>				
	Test Air Temp (degrees F.)	<u>75.3</u>				
	Relative Humidity (%)	<u>45.3</u>				
	Barometric Pressure (In. Hg.)	<u>29.21</u>				
Media Resistance Data	Resistance Data (" H₂O)					
	FPM	2.63	5.25	7.88	10.50	13.13
	Resistance	0.100	0.160	0.220	0.290	0.350

Media Resistance vs. FLOW Rate



Media Photograph		
------------------	--	--

Requestor Information	Test Requestor	<u>Joergen Poulsen</u>	Phone Number	<u>45-5495-25</u>
	Company Name	<u>JP Air Tech</u>	Email	<u>jp@jpairtech.com</u>
	Company Address	<u>Narvikvej 7 DK-4900; Denmark</u>	Date Requested	<u>6/5/2015</u>
Test Operator Information	Test Performed by:	<u>Glen Toloczko CAFS</u>	Completion Date	<u>6/12/2015</u>